

## Catalyst (drying accelerator) for THIXETANCHE & REVETANCHE PREMIUM resins.



### PURPOSE

ADJUVANT SR is a drying accelerator for the waterproofing PREMIUM resins.

It is essentially recommended in case of difficult drying conditions (temperature and/or hygrometry).

The ADJUVANT SR is imperatively used in the case of an application in thick volume (> 750 g/sqm/c) so as to guaranty the correct drying of the resin.

**NB: The addition of ADJUVANT SR considerably reduces the usable life of the products (practical usable life: 45 min with 3 % ADJUVANT SR).**

### IDENTIFICATION CHARACTERISTICS

In accordance with official standards or, if none applicable, with internal standards.

**Aspect** Translucent.

**Density**  $0.94 \pm 0.02$

**Flash Point** 27°C.

**Dosiology** Pre-dosed cans with 3 % in weight of THIXETANCHE and REVETANCHE PREMIUM resin; i.e. 0.180 kg for 6 kg or 0.750 kg for 25 kg. g.

**Classification** NF T36-005: Not classified.

**Packaging** 0.180 kg – 0.750 kg

### USE

Thoroughly mix the product in the resin with a mechanical blender (low speed) **whilst carefully scraping the inner surface and bottom of the can** until obtaining a homogeneous texture.

Regarding the use of the products, refer to the relevant technical data sheets and files.

Do not exceed the prescribed dose to avoid surface blemishes (stitches, cracks, loss of gloss, stretching...).

## CONSERVATION

- 9 months in original unopened packaging.
- Store in a cool and ventilated place..

## HEALTH, SAFETY, AND ENVIRONMENT

### Refer to

- The safety information label on the packaging.
- Safety Data Sheet (Fiche de Données de Sécurité) on the INTERNET: [www.zolpan.fr](http://www.zolpan.fr)

.....  
IMPORTANT NOTICE REGARDING THE ZOLPAN TECHNICAL SHEETS: This version cancels and supersedes previous editions. It is our customers' responsibility to check that they have the latest edition before using the product. The information given in this sheet only has an indicative value and cannot replace the specific data relating to the type and condition of the surface to be treated.



Zolpan sas : 17 quai Joseph Gillet - 69316 Lyon cedex 04 - Tél : 04 72 10 70 60 - Fax : 04 72 10 70 73  
[www.zolpan.fr](http://www.zolpan.fr) - SIREN : 972 503 387 - N° RCS : 972 503 387 RCS LYON - CAPITAL SOCIAL : 6 127 440 €