



Oil-alkyd impression paint
Fixing and absorption regulating
Suited to difficult, porous, eroded bases
Eases the application of the finishes and prevents shading phenomena

GENERAL FEATURES

PURPOSE	Impression for non alkaline bases of varying absorption capacity before rendering, filling, finishes with paint, wallpaper, wall covering, etc.
Aspect in packaging	Semi-fluid paint
Aspect Dry	Matt
Density	1.53 ± 0.05
Dry matter	78 ± 2 %
VOC concentrations	350 g/l max. EU threshold value for this product (cat A/g): 350 g/l (2010)
Dry time	Impervious to dust: 4 hours
(20°, 65% RH)	Dry / Recoatable: 24 hours
Coverage	7 to 8 sqm/kg over smooth base
Classification	NF T36-005: Family I, class 4a
Colours	White
Packaging	25 kg
Conservation	24 months in unopened original packaging Store in a cool and ventilated room

USE

Surfaces, preparatory work and application conditions must comply with the applicable standards/DTU (French standards)

SURFACES	Traditional building bases, bare or coated with old adhesive paints in good condition Do not use over fresh concrete and derived products (pH > 9) For outdoor use, the surface must be rapidly covered with a finish
Preparatory work	Bases must be sound, dry, cohesive and consistent with the product application Brush, scrape or wash to remove dirt and blistered, chipped or non-cohesive parts
Finishing	1 coat in regular application
Equipment	Anti-drop roller, brush
Dilution	Product ready for use
Equipment cleaning	White Spirit immediately after use

HEALTH & SAFETY

Refer to:

* The safety information label on the packaging

* Safety Data Sheet (Fiche de Données de Sécurité) on the INTERNET: www.zolpan.fr

Technical Data Sheet n° 2176

Issue date: **May 2004**

Last modified: **June 2012**

NB: Cancels and supersedes previous editions. It is our customers' responsibility to check that they have, the latest version before using the product.

The information given in this sheet only has an indicative value and cannot replace the specific data relating to the type and condition of the surface to be treated.