



**Acrylsiloxane mixed fixing impression
in solvent phase
For diverse, porous or eroded bases
Fixing, waterproof, microporous
Smooth matt finish**

PURPOSE Fixing impression and opacifying waterproof undercoat, aimed at regulating the of difficult bases in façade works.

Endowed with a high micro-permeable structure and excellent consolidating power of the bases, - enables to optimise the binding with the surface while preserving the essential characteristics of siloxane finishes (water steam permeability, liquid water impermeability). Particularly suited for the application of siloxane finishes such as SILEXTRA LISSE or GRANITÉ

Also perfectly compatible with the range of other traditional finishes

SURFACES Coherent, potentially porous or eroded bases: concrete, lime or cement rendering, mortar made of Parisian plaster, bricks, limestone, etc.

Approved construction boards for light buildings (wood and derived products, fibre cement, wood cement or polymer composite, etc.)

Old adherent coating, potentially displaying residual chalking, mineral paints

- MAIN FEATURES**
- * Excellent consolidating power of the bases
 - * High opacity and wide range of colours enabling you to save one coat
 - * Recoatable with any kind of paint
 - * Water steam permeability

IDENTIFICATION CHARACTERISTICS	In accordance with official standards or, if none applicable, with internal standards
Aspect	Semi-thick paint
Dry matter	* in weight: 71 ± 2 % * in volume: 45 ± 2 %
Density	1.48 ± 0.05
Flash point	> 38°C
VOC concentrations	Max. 480 g/l. EU threshold value for this product (A/h cat): 750 g/l
Dry time (20°C, 65 % RH)	Dry: 2 hours Recoatable: 24 hours <i>Drying delayed by cold and damp weather</i>
Coverage	5 to 6 sqm/l over smooth surface (250 to 300 g/sqm) <i>Depends on the type and condition of the surface</i>
Classification	NF T36-005: Family I class 7b1 / 10c

USE Surfaces, preparatory work and application conditions must comply with the applicable standards/DTU (French standards).

BASE PREPARATION Bases must be sound, dry, cohesive and consistent with the product application

* New bases: gin, dust thoroughly. Wash with HP if the brushing is insufficient, dry

* Old, bare or already coated bases:

. Remove non adherent parts through brushing, sanding, scraping, HP washing, etc.

Complete descaling of the coating if necessary

. Removal of microorganisms: FONGIMOUSSE PLUS

. Smoothing, surfacing: ARMATERM COLLE or COLLE POWDRE

* Metallic parts (degreased, derusted): adapted primer (PRIMAIRE PAH or UNIVERSEL)

* Aerated concrete: ZOLPAFIX 100 impregnation

PRODUCT APPLICATION

Process 1 regular cross-coat of the same shade as the finish to obtain a homogenous opacity

Equipment Long pile roller, brush, spray gun

Dilution Product ready for use

Equipment cleaning WHITE SPIRIT, immediately after use

Application conditions Ambient and surface temperature above 5°C (caution if T > 35°C)

Dry weather, sheltered from strong winds and direct sunlight

COLOURS ZOLPACRHOM 3 System (white / PA base and ME base)

PACKAGING 4 L - 16 L

CONSERVATION 24 months in unopened original packaging

Store in a cool and ventilated place

HEALTH AND SAFETY Refer to:

* The safety information label on the packaging

* Safety Data Sheet (Fiche de Données de Sécurité) on the INTERNET: www.zolpan.fr

Technical Data Sheet n° 2207

Issue date: May 1996

Last modified: June 2012

NB: Cancels and supersedes previous editions. It is our customers' responsibility to check that they have, the latest version before using the product.

The information given in this sheet only has an indicative value and cannot replace the specific data relating to the type and condition of the surface to be treated.

