



**Thixotropic façade paint
with acrylic copolymers in solution
High-finish refacing works
Application by cold weather
Excellent microporosity
Matt finish**

PURPOSE High-finish refacing works over a diversity of bases

SURFACES Usual building bases conveniently prepared
Approved construction boards for light buildings (wood and derived products, fibre cement, wood-cement composite or polymer wood, etc.)
Old adherent paints in good condition
NB: Do not use over old façade waterproofing systems

MAIN FEATURES

- * Respect and enhancement of the material
- * Excellent adherence over difficult bases
- * Very good refractory life over alkaline surfaces
- * High build and opacifying power
- * Excellent film microporosity (equivalent air layer: 0.3 m)
- * Good resistance to weathering and UV rays
- * Applicable by cold weather and over non frozen surface possible
- * Rapidly impervious to rain and dry

IDENTIFICATION CHARACTERISTICS In accordance with official standards or, if none applicable, with internal standards

Aspect	Semi-thick paint
Gloss	BS 60° < 3
Dry matter	* in weight: 71 ± 2 % * in volume: 44 ± 2 %
Density	1.44 ± 0.05
Flash point	> 38°C
VOC concentrations	Max. 430 g/l. EU threshold value for this product (A/c cat): 430 g/l
Dry time (20°C, 65 % RH)	Impervious to dust: 1/2 hour Dry: 2 hours Recoatable: 24 hours <i>Drying delayed by cold and damp weather</i>
Coverage	6 to 8 sqm/l per coat, depending on the surface nature and condition
Classification	NF T36-005: Family I class 7b1 XP T34-722: Class D2 EN 1062.1: E3 V2 W3 A0

USE Surfaces, preparatory work and application conditions must comply with the applicable standards/DTU (French standards).

BASE PREPARATION Bases must be sound, dry, cohesive and consistent with the product application

* Depending on the cases, they may require brushing, sanding, scraping, pickling, HP washing, leaching, etc. to eliminate all traces of dirt as well as chipped, friable, non-cohesive, glossy, etc. parts.

* Removal of microorganisms: FONGIMOUSSE PLUS

* Smoothing, filing, dressing: ARMATERM COLLE or COLLE POUDRE

* Metal accessories (degreased, derusted): direct application or suited impression, depending on environment aggressiveness

* Direct application over prepared, bare materials or coated with old adhesive paints

PRODUCT APPLICATION

Process

2 coats tone-on-tone

Process by thick coats and even without stretching

NB: the STYZOL THIXO + ZOLPAN MAT system may be preferred, in some cases, to the STYZOL THIXO two-coat system, in particular for the execution of finishes in strong colours in case of sun exposition

Equipment

Brush, long pile roller, airless sprayer

Dilution

Product ready for use

Equipment cleaning

WHITE SPIRIT, immediately after use

Application conditions

Applicable by cold weather, non frozen surface (caution if $T > 35^{\circ}\text{C}$)

Dry weather, sheltered from strong winds and direct sunlight

COLOURS ZOLPACRHOM 3 System (white / PA base)

PACKAGING 1 L (white) - 4 L - 16 L

CONSERVATION 24 months in unopened original packaging
Store in a cool and ventilated place

HEALTH AND SAFETY

Refer to:

* The safety information label on the packaging

* Safety Data Sheet (Fiche de Données de Sécurité) on the INTERNET: www.zolpan.fr

Technical Data Sheet n° 2439

Issue date: June 1994

Last modified: June 2012

NB: Cancels and supersedes previous editions. It is our customers' responsibility to check that they have, the latest version before using the product.

The information given in this sheet only has an indicative value and cannot replace the specific data relating to the type and condition of the surface to be treated.

