



## Thick plastic coating to be rolled Fungistatic quality Fine-grained rustic finish

---

**PURPOSE** \* Masonry protection and decoration in new or maintenance works  
Outdoors: building façades  
Indoors: private or common areas, passage areas (corridors, entrance halls, staircases etc.)

---

**SURFACES** Usual building bases conveniently prepared  
Old adherent paints in good condition

---

**MAIN FEATURES**

- \* Protection of porous or cracked surfaces against weathering
- \* Good steam permeability
- \* Excellent resistance to the development of microorganisms
- \* Easy and rapid use
- \* High wet-edge time
- \* Product in aqueous phase: easy and safe use, environmentally friendly

---

**IDENTIFICATION CHARACTERISTICS** In accordance with official standards or, if none applicable, with internal standards

**Aspect** Soft granular paste

**Dry matter** \* in weight:  $78 \pm 2 \%$   
\* in volume:  $61 \pm 2 \%$

**Density**  $1.56 \pm 0.10$

**Flash point** n/a

**VOC concentrations** Max. 30 g/l. EU threshold value for this product (A/a cat): 30 g/l

**Dry time (20°C, 65 % RH)** Dry: 4 hours  
Recoatable: 24 hours minimum  
Hard: 1 week  
*Drying delayed by cold and damp weather*

**Consumption** About 1.5 kg/sqm

**Classification** **NF T36-005:** Family II class 2b  
**XP T34-722:** Class D3  
**EN 1062-1:** E5 V1 W3 A0

---

**USE** Surfaces, preparatory work and application conditions must comply with the applicable standards/DTU (French standards).

**BASE PREPARATION** Bases must be sound, dry, cohesive and consistent with the product application  
They may require, depending on the cases, dusting, brushing, sanding, scraping, pickling, HP washing, leaching, etc. so as to eliminate any trace of dirt and chipped, friable, non-cohesive, glossy, etc. parts.

- \* Removal of microorganisms: FONGIMOUSSE PLUS
- \* Metallic parts (degreased, derusted): adapted primer (PRIMAIRE PAH or UNIVERSEL)
- \* Concrete and derived products, old adherent paints: diluted ZOLGRAIN impression (ca. 15 % water) over sound bases or SWEDAFIX GRANITÉ / ZOLPAFIX GRANITÉ, dep. on the use (Ind/Out), over porous or slightly non-cohesive bases
- \* Remove blisters with the RPE if possible, otherwise, rake/dress with ARMATERM COLLE or COLLE POUDRE (outdoor) and FILLEX or CILD (indoor) and diluted ZOLGRAIN impression
- \* Plasters and derived products: SWEDAFIX GRANITÉ impression
- \* Wood and derived products: PROLOG / ZOLPAPRIM GRANITÉ impression, dep. on the use (Ind/Out)

## PRODUCT APPLICATION

**Process** 1 regular coat over impression of the same colour

**Equipment** \* Manual application: paste with a woollen long pile roller or with a stainless steel trowel and structure immediately by cross movements with a foam honeycomb roller for a traditional structure  
\* Mechanised application: projection by hopper under pressure with low output, using a spray gun of the TR type by KREMLIN for a more rounded rustic structure

**Dilution** Product ready for use en finition  
15 % d'eau en impression

**Equipment cleaning** WATER, immediately after use

**Practical advice** \* Application conditions:  
. Ambient and surface temperature above 5°C (caution if  $T > 35^{\circ}\text{C}$ )  
. Dry weather, sheltered from strong winds and direct sunlight  
\* Do not apply over a surface likely to display permanent humidity: foundations, balcony soffit, etc  
\* Use a similar batch for the whole unit area in order to avoid shade differences due to the natural mineral origin of the aggregates  
\* Allow appropriate protection in the coating's adherence plan (base flashing, composition flashing) against rainwater running  
\* Proceed continuously and per unit area so as to avoid visible joints. Otherwise, plan a division into panels (for ex.: treatment of large surfaces)

**COLOURS** ZOLPACRHOM 3 System (white / PA base)  
We advise against the use of colours displaying a sunlight absorption coefficient above 70 % for surfaces exposed to sunlight

**PACKAGING** 5 kg - 25 kg

**CONSERVATION** 24 months in unopened original packaging  
Store away from frost and temperatures above 35°C

**HEALTH AND SAFETY** Refer to:  
\* The safety information label on the packaging  
\* Safety Data Sheet (Fiche de Données de Sécurité) on the INTERNET: [www.zolpan.fr](http://www.zolpan.fr)

Technical Data Sheet n° 2307

**Issue date: June 1994**

**Last modified: June 2012**

*NB: Cancels and supersedes previous editions. It is our customers' responsibility to check that they have, the latest version before using the product.*

*The information given in this sheet only has an indicative value and cannot replace the specific data relating to the type and condition of the surface to be treated.*

